

TECHNICAL SHEET



Article: **B0953 QUASAR**
 Norm: **UNI EN ISO 20345:2012**
 Safety Class: **S1 P SRC**

Footwear height: **Mod. A, H 99 mm (< 113 mm, Rif. EN 20345-5.2.2)**

Width: **12**

Construction: **STROBEL; PU SOLE monodensity**

Cleaning and maintenance: *Use only soft brushes and water. Do not use substances like alcohol, thinners, gasoline, oil or any other chemicals. Keep the footwear, dry and clean, in a proper place at room temperature.*

Suggested fields: **Mechanics, buildings, leight industry, craftsman, automotive, assembly lienes.**

Entire footwear: components				
Component	Description	Value	Norm Requirements	EN 20345
Composit toe-cap Slimcap	Impact resistance (200 J)	14,0 mm	≥ 14 mm	5.3.2.3
	• Free height after impact			
Sole (SRC)	Compression resistance (15 kN)	14,5 mm	≥ 14 mm	5.3.2.4
	• Free height after compression			
Fresh'n Flex (P)	Slip resistance			
	• SRA – sole (entire sole)	0,48	≥ 0,32	5.3.5.4
	• SRA – heel (angle 7°)	0,45	≥ 0,28	5.3.5.4
	• SRB – sole (entire sole)	0,22	≥ 0,18	5.3.5.4
Footbed (A)	• SRB – heel (angle 7°)	0,20	≥ 0,13	5.3.5.4
	Puncture resistance	No perforation	≥ 1100 N	6.2.1.1.2
Sole/Upper	Antistatic properties			
	• Electrical resistance	dry 4,08 x 10 ⁸ Ω	≥ 10 ⁵ Ω , ≤ 10 ⁹ Ω	6.2.2.2
Heat (HI)	Thermal insulation			
	• Insole temperature increase	N/A	≤ 22°C	6.2.3.1
Cold (CI)	• Insole temperature release	N/A	≤ 10°C	6.2.3.2
	Shock-absorption in the heel region	35 J	≥ 20 J	6.2.4
(WR)	Water resistance (Water absorption)	N/A	≤ 3 cm ²	6.2.5
(M)	Metatarsal protection	N/A	≥ 40 mm	6.2.6

Upper				
Component	Description	Value	Norm Requirements	EN 20345
Suede leather	Tear resistance	198 N	≥ 120 N	5.4.3
	Traction resistance	21 N/mm ²	≥ 15 N/mm ²	5.4.4
	Water steam permeability	3,5 mg/cm ² h	≥ 0.8 mg/cm ² h	5.4.6
	pH value	4,05	≥ 3,2	5.4.7
	Chromium VI	Not detected	Non detectable	5.4.9
	Water passed	N/A	≤ 0.2 g	6.3
	Water absorption	N/A	≤ 30%	6.3

Lining				
Component	Description	Value	Norm Requirements	EN 20345
3D hi-tech fabric	Tear resistance	45 N	≥ 15 N	5.5.1
	Abrasion resistance	<ul style="list-style-type: none"> Dry : the surface shows no holes humid: the surface shows no holes 	No holes till 51.200 cycles	5.5.2
	Water steam release	21,0 mg/cm ² h	≥ 2,0 mg/cm ² h	5.5.3
	pH value	N/A	Non detectable	5.5.4
	Chromium VI	N/A	Non detectable	5.5.5

Insole				
Component	Description	Value	Norm Requirements	EN 20345
Fresh'n Flex	Thickness	3,7 mm	≥ 2,0 mm	5.7.1
	pH value	N/A	Non detectable	5.7.2
	Water absorption	82 mg/cm ²	≥ 70 mg/cm ²	5.7.3
	Water release	90 %	≥ 80 %	5.7.3
	Abrasion resistance (after 400 cycles)	No damage	Damage ≤ to norms reference	5.7.4.1
	Chromium VI	N/A	Not detectable	5.7.5

Removable footbed				
Component	Description	Value	Norm Requirements	EN 20345
Anatomical, breathable, textile and expanded polymeric material	Thickness	3,0±0,5 mm	N/A	5.7.1
	pH value	N/A	Non detectable	5.7.2
	Water absorption	Permeable	Permeable or ≥ 70mg/cm ²	5.7.3
	Water release	Permeable	Permeable or ≥ 80%	5.7.3
	Abrasion resistance	No damage	Dry No holes till 25600 cycles Humid no holes till 12800 cycles	5.7.4.2
	Chromium VI	N/A	Non detectable	5.7.5

Suola					
Component	Description	Value	Norm Requirements	EN 20345	
PU monodensity sole	Sole thickness without profile	6,5 mm	≥ 4 mm	5.8.1.1	
	Profile height	4,5 mm	≥ 2,5mm	5.8.1.3	
	Tear resistance	6,2 kN/m	≥ 5 kN/m	5.8.2	
	Abrasion resistance	<ul style="list-style-type: none"> relative volume loss 	100 mm ³	≤ 250 mm ³	5.8.3
	Flexion resistance	<ul style="list-style-type: none"> Notches increase after 30.000 cycles 	2,1 mm	≤ 4 mm	5.8.4
		<ul style="list-style-type: none"> Hydrolysis 	3 mm	≤ 6 mm	5.8.5
		Notches increase after 150.00 cycles	N/A	≥ 4 N/mm; (*) ≥ 3 N/mm with sole ripping	5.8.6
		(HRO) Contact heat resistance (300°C)	N/A	No damage (melting, breaking)	6.4.1
		(FO) Fuel resistance (volume changes)	6 %	≤ 12%	6.4.2

Date: 24/11/2016

Issued by: Resp.Techn. Eng. Cataldo De Luca

Signature:

